JW Max Series



n-Type Bifacial Dual Glass Mono Module

JW-HD132N 685-715W

Maximum 715W

Maximum Module 23.02%

Power Output 0~+3%

n-TOPCon



Higher Customer Value

- Lower 1st-year and annual degradation
- Lower system BOS cost, higher power generation, lower LCOE, and higher ROI
- Dual-side power generation, with up to 30% increase in backside power generation in different installation environments, further reducing overall



Higher Power Generation Gain

- Excellent IAM property and better weak illumination response
- Lower 1st-year degradation (1%) and annual degradation (0.4%)
- Lower temperature coefficient (-0.30%) and lower operating temperature, resulting in more power generation



High Reliability

- Apply lastest generation TOPCon technology with lower LID and LETID
- · Apply innovative non-destructive cutting technology to reduce the risk of
- Withstand harsh environmental conditions, such as salt mist, ammonia, PID, dust and sand, and high-temperature and high-humidity



High Safety

- Lastest TOPCon technology with no polysilicon wrap around, zero leakage current and better resistance to hot-spot.
- Pass mechanical load test of 5400Pa on the front side and 2400Pa on the back















IEC61215(2021)/IEC61730(2023)/IEC61701/IEC62716

ISO9001:2015: Quality Management System

ISO14001:2015: Environment Management System

ISO45001:2018: Occupational health and safety

IEC62941:2019: Quality system for PV module manufacturing

Linear Performance Warranty



Version 2024.01 ©Jolywood (Taizhou) SolarTechnology Co., Ltd. All rights reserved

www.jolywood.cn



Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone, Taizhou, Jiangsu Province, China, 225500

TEL: +86 523 80612799 Email: mkt@jolywood.cn

JW-HD132N n-type Bifacial Dual Glass Mono Module

Electrical Properties	STC	ė					
Testing Condition	Front Side						
Peak Power (Pmax) (W)	685	690	695	700	705	710	715
MPP Voltage (Vmp) (V)	40.36	40.52	40.68	40.84	41.00	41.16	41.32
MPP Current (Imp) (A)	16.97	17.03	17.08	17.14	17.20	17.25	17.30
Open Circuit Voltage (Voc) (V)	47.06	47.24	47.42	47.60	47.78	47.96	48.14
Short Circuit Current (Isc) (A)	18.04	18.08	18.12	18.16	18.20	18.24	18.28
Module Efficiency (%)	22.05	22.21	22.37	22.53	22.70	22.86	23.02

^{*}STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties	NMOT*						
Testing Condition	Front Side						
Peak Power (Pmax) (W)	513	517	521	524	528	532	536
MPP Voltage (Vmp) (V)	38.64	38.80	38.95	39.10	39.26	39.41	39.56
MPP Current (Imp) (A)	13.28	13.32	13.36	13.41	13.45	13.49	13.54
Open Circuit Voltage (Voc) (V)	45.06	45.23	45.41	45.58	45.75	45.92	46.09
Short Circuit Current (Isc) (A)	14.57	14.60	14.63	14.67	14.70	14.73	14.76

^{*}NMOT: Irradiance 800 W/m². Ambient Temperature 20°C. Wind Speed 1 m/s

Electrical Properties Under Different Rear Gain HD132N-700					
Power Gain (%)	Peak Power (Pmax) (W)	MPP Voltage (Vmp) (V)	MPP Current (Imp) (A)	Open Circuit Voltage (Voc) (V)	Short Circuit Current (Isc) (A)
10	770.0	40.84	18.85	47.60	19.98
15	805.0	40.94	19.66	47.70	20.84
20	840.0	40.94	20.52	47.70	21.75
25	875.0	40.94	21.37	47.70	22.65
30	910.0	41.04	22.17	47.80	23.51


Operating Properties	
Operating Temperature	-40°C∼+85°C
Maximum System Voltage	1500V (IEC)
Maximum Series Fuse Rating	35A
Bifaciality*	80%
Front Static Load	Snow load 5400Pa, Wind load 2400Pa
*Difi-lit - D (CTC) (Df+ (CTC)	Different Linear and EQ

Temperature Coefficient		
Temperature Coefficient of Pmax*	-0.300%/°C	
Temperature Coefficient of Voc	-0.250%/°C	
Temperature Coefficient of Isc	+0.045%/°C	
Nominal Operating Cell Temperature (NOCT)	42±2℃	


Specification	
Number of Cells	132pcs
Module Dimension	2384mm*1303mm*33mm
Weight	38.1kg
Front / Rear Glass*	2.0mm*2.0mm Heated strengthened glass
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +400mm/-200mm (Cable length can be customized)
Packaging Configuration	33pcs/Pallet, 594/40HQ Container

^{*}The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please alwaysobtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein.


Engineering Drawing (unit: mm)



Characteristic Curves HD132N-700



I-V Characteristics At Different Irradiations



20 18 16 14 -10°C Current (A) 12 -25°C 10 40°C 8 -55°C -70°C 0 20 30 40 60 0 10 50 Voltage (V)

I-V Characteristics At Different Temperatures

www.jolywood.cn



*Temperature Coefficient of Pmax±0.03%/°C

Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone, Taizhou, Jiangsu Province, China, 225500

TEL: +86 523 80612799 Email: mkt@jolywood.cn

